

# Corrosion Rate Table

Alloy	Weight loss after 24hrs (%)	
	Struvicide™ O Remove	Hydrochloric Acid (31%)
Stainless Steel	0.01	43.7
6061T6 Bare Aluminum	0.10	100.00
1010 Carbon Steel	0.05	36.42
Zinc	0.71	30.27
Brass	0.01	0.15