

Corrosion Rate Table

Alloy	Weight loss after 24hrs (%)	
	Struvicide™ Soak	Hydrochloric Acid (31%)
Stainless Steel	0.06	43.7
6061T6 Bare Aluminum	47.43	100.00
1010 Carbon Steel	0.05	36.42
Zinc	0.58	30.27
Brass	0.03	0.15